

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 727 413 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
21.08.1996 Bulletin 1996/34

(51) Int. Cl.⁶: C07C 259/18, C08G 73/08,
C08K 5/33

(21) Application number: 96100416.5

(22) Date of filing: 12.01.1996

(84) Designated Contracting States:
DE GB IT

(30) Priority: 16.02.1995 JP 51977/95

(71) Applicant: NIPPON MEKTRON, LTD.
Minato-ku Tokyo (JP)


(72) Inventors:
• Satoru, Saito
Kitaibaraki city, Ibaraki (JP)
• Haruyoshi, Tatsu
Hitachi city, Ibaraki (JP)
• German, Lev Solomonovich
Deceased (RU)

• Zeifman, Yuri V.
Kwartira 61, 117571, Moscow (RU)
• Postovoi, Sergei A.
Pushkino, 141500, Moscow region (RU)
• Sterlin, Sergei R.
Kwartira 24, 117602, Moscow (RU)

(74) Representative: Hansen, Bernd, Dr. Dipl.-Chem.
et al
Hoffmann, Eitle & Partner,
Patentanwälte,
Arabellastrasse 4
81925 München (DE)

(54) Bisamidoxime compound, process for preparing the same and a fluorine-containing elastomer composition comprising the same

(57) When a novel bisamidoxime compound represented by the following general formula:



where R is an alkylidene group having 1 to 6 carbon atoms, or a perfluoroalkylidene group having 1 to 10 carbon atoms, is used as a vulcanizing agent for fluorine-containing elastomers having cyano groups as cross-linkable groups, the resulting vulcanizates having a satisfactory compression set are obtained without any problem of processability such as roll kneadability, etc.

EP 0 727 413 A1

Description

BACKGROUND OF THE INVENTION

1. FIELD OF THE INVENTION


The present invention relates to a bisamidoxime compound, a process for preparing the same and a fluorine-containing elastomer composition comprising the same, and more particularly a novel bisamidoxime compound, a process for preparing the same and a fluorine-containing elastomer composition comprising a fluorine-containing elastomer having cyano group as cross-linkable groups and the bisamidoxime compound as a vulcanizing agent.

2. RELATED ART

JP-A-59-109546 discloses a fluorine-containing elastomer composition comprising a terpolymer of tetrafluoroethyleneperfluoro(methyl vinyl ether)-perfluoro unsaturated nitrile compound represented by the following general formula:




where n is an integer of 1 to 2 and m is an integer of 1 to 4, and a bis(aminophenyl) compound represented by the following general formula:



wherein A is an alkylidene group having 1 to 6 carbon atoms, a perfluoroalkylidene group having 1 to 10 carbon atoms, SO_2 , O, CO or a carbon-carbon bond of directly bonding two benzene rings, and X and Y are hydroxyl groups or amino groups, as a curing agent. However, the vulcanisation products resulting from vulcanization of such a fluorine-containing elastomer composition have no satisfactory compression set.

The present inventors proposed a bisamidrazone compound represented by the following general formula:




as a novel vulcanizing agent capable of giving a vulcanization product having a satisfactory compression set when used as a vulcanizing agent for the fluorine-containing elastomer having cyano groups as cross-linkable groups (Japanese Patent Application No.282943/1994). The proposed bisamidrazone compound can give a vulcanization product having a satisfactory compression set when used as a vulcanizing agent for the fluorine-containing elastomer having cyano groups as cross-linkable groups, but has a higher reactivity to the cyano groups as cross-linkable groups and sometimes generates scorching, depending on kneading temperature, shearing force, etc. when the composition is kneaded by two roll mills, etc. prior to the vulcanization.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a novel vulcanizing agent compound capable of giving a vulcanizate having a satisfactory compression set without any problems of processing such as roll kneadability, etc. when a fluorine-containing elastomer having cyano groups as cross-linkable groups is kneaded and vulcanized.


According to the present invention, a novel bisamidoxime compound represented by the following general formula:



where R is an alkylidene compound having 1 to 6 carbon atoms, or a perfluoroalkylidene compound having 1 to 10 carbon atoms, is provided and can serve as a suitable vulcanization agent for fluorine-containing elastomers having cyano group as cross-linkable groups.


DETAILED DESCRIPTION OF THE INVENTION

The present bisamidoxime compound can be readily prepared by reaction of a bis(cyanophenyl) compound represented by the following general formula:



with a hydroxylamine or its salt.

In the bis(cyanophenyl) compound represented by the foregoing general formula, R is preferably an alkylidene group such as an isopropylidene group or a perfluoroalkylidene group such as a perfluoroisopropylidene group, and compounds represented by the following general formula are preferably used:






Reaction of the bis(cyanophenyl) compound with the hydroxylamine or its salt such as hydrochloride, sulfate etc. can be readily carried out in a solvent such as methanol, ethanol or the like generally at the reflux temperature, using the hydroxylamine or its salt in a molar amount by at least twice more than that of the bis(cyanophenyl) compound and an aqueous solution of a basic substance such as sodium hydroxide, potassium hydroxide or the like as a catalyst.

The thus obtained bisamidoxime compound is used as a vulcanising agent for a fluorine-containing elastomer having cyano groups as cross-linkable groups. The fluorine-containing elastomer for use in the present invention includes, for example, a terpolymer consisting of 45 to 75% by mole of tetrafluoroethylene, 54.8 to 20% by mole of perfluoro(lower alkyl vinyl ether) and 0.2 to 5% by mole of perfluoro unsaturated nitrile compound.

As the perfluoro(lower alkyl vinyl ether), perfluoro (methyl vinyl ether) is usually used.

As the perfluoro unsaturated nitrile compound serving as a cross-linking site monomer, the following compounds are used:





15

24

24

34

34

EXAMPLE 1

45



55

Elemental analysis (C ₁₇ H ₁₄ F ₆ N ₄ O ₂):			
Calculated	C 48.57%,	H 3.33%,	F 27.14%
Found	C 48.65%,	H 3.23%,	F 26.48%

Mass spectrum (m/z): 420(M⁺)

REFERENCE EXAMPLE 1

51kg of distilled water, 900g of ammonium perfluorooctanoate and 782g of potassium dihydrogen phosphate were charged into a stainless steel autoclave having a net capacity of 100 liters, and then the inside gas in the autoclave was replaced with a nitrogen gas. Then, the autoclave was subjected to pressure reduction, and the following compounds were successively charged into the autoclave:

Tetrafluoroethylene [TFE]	1.57kg
Perfluoro(methyl vinyl ether) [FMVE]	1.90kg
Perfluoro(5-cyanopentyl vinyl ether) [CPVE]	90g

Then, the autoclave was heated to 60°C, and 5 liters of an aqueous solution containing 150g of ammonium persulfate and 26g of sodium sulfite was added thereto to initiate polymerization reaction.

During the polymerization reaction, TFE, FMVE and CPVE were additionally supplied to the autoclave at feed rates of 1.2 kg/hr, 1.4 kg/hr and 75 g/hr, respectively, to maintain the inside pressure of the autoclave at 8.0-9.0 kg/cm² gage. 7 hours after the start of polymerization reaction, the additional supply was discontinued and the autoclave was kept in that state for one hour. Then, the autoclave was cooled and the residual gas was purged therefrom, whereby 78kg of aqueous latex containing 27% by weight of solid matters was obtained.

Then, the thus obtained aqueous latex was added to a mixture consisting of 80 liters of an aqueous 5 wt.% magnesium chloride solution and 80 liters of ethanol to coagulate the latex. Then, the aggregate was washed with water and dried at 80°C under the atmospheric pressure for 70 hours, whereby 19.8 kg of white rubbery terpolymer A was obtained (yield: 88%).

It was found by ultraviolet spectrum and NMR analysis that the thus obtained rubbery terpolymer had the following composition.

TFE	68.8 mol. %
FMVE	30.0 mol. %
CPVE	1.2 mol. %

REFERENCE EXAMPLE 2

55kg of distilled water, 1,800g of ammonium perfluorooctanoate and 782g of potassium dihydrogen phosphate were charged into a stainless steel autoclave having a net capacity of 100 liters, and then the inside gas in the autoclave was replaced with a nitrogen gas. Then, the autoclave was subjected to pressure reduction. Then, the following compounds were successively charged into the autoclave:

Tetrafluoroethylene (TFE)	1.26kg
Perfluoro(methyl vinyl ether) [FMVE]	1.30kg
Perfluoro(2-cyano-3,7-dioxa-8-nonene) [CEPVE]	170g

Then, the autoclave was heated to 60°C, and 5 liters of an aqueous solution containing 200g of ammonium persulfate and 36g of sodium sulfite was added thereto to initiate polymerization reaction.

During the polymerization reaction, TFE, FMVE and CEPVE were additionally supplied to the autoclave at feed rates of 2.09 kg/hr, 2.25 kg/hr and 267 g/hr, respectively, to maintain the inside pressure of the autoclave at 8.0-9.0 kg/cm² gage. 4.5 hours after the start of polymerization reaction, the additional supply was discontinued and the autoclave was kept in that state for one hour. Then, the autoclave was cooled and the residual gas was purged therefrom, whereby 78kg of aqueous latex containing 28% by weight of solid matters was obtained.

Then, the thus obtained aqueous latex was added to a mixture consisting of 80 liters of an aqueous 5 wt.% magnesium chloride solution and 80 liters of ethanol to coagulate the latex. Then, the aggregate was washed with water and dried at 80°C under the atmospheric pressure for 70 hours, whereby 20.9 kg of white rubbery terpolymer B was obtained (yield: 89%).

It was found by infrared spectrum and NMR analysis that the rubbery terpolymer (η_{sp}/c : 0.59 dl/g) had the following composition.

TFE	72.1 mol.%
FMVE	25.5 mol.%
CEPVE	2.4 mol.%


EXAMPLE 2

100 parts by weight of the rubbery terpolymer A or B obtained in Reference Example 1 or 2, respectively, was admixed with 20 parts by weight of MT carbon black and 0.5 parts by weight of 2,2-bis(4-carboxyphenyl)hexafluoropropane bisamidoxime, and the mixture was kneaded in two roll mills. Then, the kneaded mixture was press-vulcanized at 180°C for 30 minutes and then oven-vulcanized in a nitrogen atmosphere successively stagewise under the following conditions:

- 1st stage: Keeping at 90°C for 4 hours,
- 2nd stage: Heating to 204°C over 6 hours,
- 3rd stage: Keeping at 204°C for 18 hours,
- 4th stage: Heating to 288°C over 6 hours, and
- 5th stage: Keeping at 288°C for 18 hours.

COMPARATIVE EXAMPLE

In Example 2, the same amount of 2,2-bis(4-carboxyphenyl)hexafluoropropane bisamidrazone of the following chemical formula was used in place of 2,2-bis(4-carboxyphenyl)hexafluoropropane bisamidoxime.



EP 0 727 413 A1

The vulcanisation products obtained in Example 2 and Comparative Example were subjected to determination of the following measurement items:

Normal state physical properties:

Hardness according to DIN 53505

Tensile test according to DIN 53504 for 100% modulus, tensile strength and elongation

Heat ageing test:

Normal state physical properties after ageing in air at 300°C for 70 hours.

Compression set:

ASTM Method B/P-24 O-ring

Hot water resistance:

Percent volume swelling after immersion in pressurized water at 200°C for 70 hours.

Vulcanized sheet surface:

Visual determination of the presence of surface unevenness

Results of determination are shown in the following Table.

TABLE


Measurement items	Example 2 Terpolymer		Comp. Ex. Terpolymer	
	A	B	A	B
[Normal state physical properties]				
Hardness	73	72	75	72
100% modulus (MPa)	8.0	7.6	9.3	9.0
Tensile strength (MPa)	21.1	17.2	21.6	21.2
Elongation (%)	170	160	160	170
[Heat ageing test]				
Hardness	72	71	74	72
100% modulus (MPa)	5.6	6.1	8.0	6.9
Tensile strength (MPa)	20.9	15.0	21.4	18.4
Elongation (%)	211	170	190	211
[Compression set]				
300°C for 70 hours (%)	35	30	32	36
[Hot water resistance]				
Percent volume swelling (%)	4.6	1.4	3.6	1.9
[Vulcanized sheet surface]				
Presence of surface unevenness	none	none	none	existed

When a bisamidrazone compound is used as a vulcanizing agent, vulcanization reaction sometimes proceeds partially during the roll kneading. The resulting composition has a poor roll kneadability, sometimes resulting in fluctuations in the physical properties of the final vulcanizates. In the press molding, poor flowing, rough vulcanization molding product surfaces after the secondary vulcanization, deformation of vulcanization molding products, etc. are sometimes observable.

When a bisamidoxime compound is used as a vulcanizing agent on the other hand, good roll kneadability and press formability can be obtained without any poor flowing, rough vulcanization molding product surfaces, deformation of vulcanization molding products, etc. Physical properties are no less than those obtained when the bisamidrazone compound.


Claims

1. A bisamidoxime compound represented by the following general formula:




where R is an alkylidene group having 1 to 6 carbon atoms, or a perfluoroalkylidene group having 1 to 10 carbon atoms.

2. A bisamidoxime compound represented by the following general formula:




where R is an alkylidene group having 1 to 6 carbon atoms, or a perfluoroalkylidene group having 1 to 10 carbon atoms.


3. A bisamidoxime compound represented by the following formula:




4. A bisamidoxime compound represented by the following formula:



5. A process for preparing a bisamidoxime compound represented by the following general formula:




where R is an alkylidene group having 1 to 6 carbon atoms, or a perfluoroalkylidene group having 1 to 10 carbon atoms, which comprises reacting a bis(cyanophenyl) compound represented by the following general formula:



where R has the same meanings as defined above, with hydroxylamine or its salt.

6. A fluorine-containing elastomer composition, which comprises a fluorine-containing elastomer having cyano groups as cross-linkable groups and a bisamidoxime compound represented by the following general formula:



where R is an alkylidene group having 1 to 6 carbon atoms, or a perfluoroalkylidene group having 1 to 10 carbon atoms, as a vulcanizing agent.

7. A fluorine-containing elastomer composition according to Claim 3, wherein a fluorine-containing elastomer is a terpolymer consisting of 45 to 75% by mole of tetrafluoroethylene, 54.8 to 20% by mole of perfluoro(lower alkyl vinyl ether) and 0.2 to 5% by mole of perfluoro unsaturated nitrile compound.
8. A fluorine-containing elastomer composition according to Claim 3, wherein about 0.2 to about 5 parts by weight of the bisamidoxime compound is used per 100 parts by weight of the fluorine-containing elastomer having cyano groups as cross-linkable groups.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 10 0416

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	US-A-4 273 918 (R.W. ROSSER ET AL) * claim 1 *	6	C07C259/18 C08G73/08 C08K5/33
A	US-A-4 145 524 (R.A. FROSCH ET AL) * claims 1,6 *	1,6	
A	EP-A-0 601 977 (CIBA-GEIGY) * claim 1 *	1	
A	DATABASE WPI Section Ch, Week 8042 Derwent Publications Ltd., London, GB; Class C, AN 80-74697 XP002002728 & SU-A-718 461 (IVAN SYNTH LEATH) , 1 March 1980 * abstract *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C07C C08G C08K
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 10 May 1996	Examiner Kapteyn, H
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 150 (01.92) (P0401)